

# GEECON PINK

## IDENTIFICATION

Geecon Pink, E 6013

## CLASSIFICATION

AWS/SFA 5.1: E 6013, IS: 814 - 2004: ER-4211X

BS: E4322R21, DIN: E 4322R322

## DESCRIPTION

An extruded rutile-based, medium heavy coated electrode.

It is weld able in all positions with minimum spatter. It has excellent striking and restricting properties. The weld bead is uniformly rippled and shining. The slag is compact, uniform and easy to remove and deposited weld metal is of radiographic quality.

## WELD METAL ANALYSIS (RANGE) %

C	Mn	Si	S	P
0.10 max	0.35 - 0.60	0.15 - 0.50	0.03 max	0.03 max


## MECHANICAL PROPERTIES (RANGE)

TS (MPa)	PS (MPa )	EL (%) (L=4D)	CVN Impact Value	
			Temp	Joules
460 - 560	370 - 480	22 - 30	0°C	47 - 90

## TYPICAL APPLICATIONS

Suitable for radiographic quality welding on critically stressed joints. Applicable for repair welding/ surfacing of naval steels, boiler steels and structural steels. Widely used in welding of steel structures, heavy-duty boilers and pressure vessels, heat exchanges, ships and barges, pipelines, storage tanks, bridges, railway coaches etc.

## WELDING POSITION :



## PACKING PARAMETERS

Size (mm)	Length (mm)	Amps AC / DC (+/-)	Packing / Box (kg)	Packing / Box (Pcs)
2.5	350	60 - 85	5 x 4 = 20	225 x 4=900
3.15 / 3.20	350	95 - 130	5 x 4 = 20	120 x 4 = 480
3.15 / 3.20	450	95 - 130	5 x 4 = 20	120 x 4 = 480
4	450	130 - 180	5 x 4 = 20	80 x 4 = 320
5	450	200 - 240	5 x 4 = 20	50 x 4 = 200