

# **GETIG 25.9.4L**

### A SUPER DUPLEX STAINLESS STEEL TIG WIRE

### **IDENTIFICATION**

Getig 25.9.4L, ER 25.9.4

## **CLASSIFICATION**

AWS/SFA 5.9: ER 25.9.4

#### **DESCRIPTION**

Getig 25.9.4L is a tig wire designed to match similar alloys. The wire gives matching strength and corrosion resistance in the solution treated condition but can also be used in the as-welded condition. Nitrogen and nickel contents are controlled to give a balanced duplex structure to minimize the risk of cracking, particularly in highly restrained welds.

## **CHEMICAL ANALYSIS (RANGE) %**

С	Cr	Ni	Mn	Si	W	S	P	Mo	Cu	N
0.03	24.0 - 27.0	8.0 - 10.5	0.5 - 2.50	1	1	0.02	0.03	2.5-4.5	1.5	0.20 - 0.30
Max				max	max	max	max		max	

## **MECHANICAL PROPERTIES (RANGE)**

UTS (MPa)	EL (%) (L=4D)
760 Min	18 Min

## TYPICAL APPLICATIONS

Pumps and valves, corrosion / wear resisting parts and process equipment for use in offshore oil and gas industries, pulp, paper and textile industries, and chemical and petrochemical plant.

### MATERIALS TO BE WELDED

- SAF 2507, ASTM S-32750, S-32760
- ASTM A351, A744 (cast) CD4MCu, UNS J93370.
- ASTM A240 (wrought) UNS S32550
- BS 3146- ANC 21, BS 3100 332C13
- DIN 1.4515, 1.4517
- Steel EN 1.4410, NF 23CND 25-06AZ, SS2328

#### **MICROSTRUCTURE:**

In the solution treated condition the micro- structure is duplex with about 30-60% ferrite dependent upon dilution.

**INTERPASS TEMPERATURE:** 100°C max

**HEAT INPUT** : 0.5 - 1.5 kJ/mm

**SCALING TEMPERATURE:** Approx 850°C (air)

GEE LIMITED | www.geelimited.com



Very good resistance to pitting and stress corrosion cracking in Chloride containing environments. Pitting resistance in accordance with ASTM G-48A better than 40°C.

## **PACKING PARAMETERS**

Size (mm)	Length (mm)	Packing / Pkt (kg)	Packing / Box (kg)
1.6	1000	5	$5 \times 4 = 20$
2	1000	5	$5 \times 4 = 20$
2.40 / 2.50	1000	5	$5 \times 4 = 20$
3.15 / 3.20	1000	5	5 x 4 = 20