

GETIG 25.9.5L

A SUPER DUPLEX STAINLESS STEEL TIG WIRE

IDENTIFICATION

Getig 25.9.5L, ER 29.9.5

CLASSIFICATION

AWS/SFA 5.9: ER 25.9.5

DESCRIPTION

Getig 25.9.5 is a tig wire designed to match similar alloys. The wire gives matching strength and corrosion resistance in the solution treated condition but can also be used in the as-welded condition. Nitrogen and nickel contents are controlled to give a balanced duplex structure to minimize the risk of cracking, particularly in highly restrained welds.

CHEMICAL ANALYSIS (RANGE) %

C	Cr	Ni	Mn	Si	W	S	P	Mo	Cu	N
0.03 max	24.0 - 27.0	8.0 - 10.5	0.5 - 2.50	1 max	1 max	0.02 max	0.03 max	3.5 - 4.5	1.5 max	0.20 - 0.30

MECHANICAL PROPERTIES (RANGE)

UTS (MPa)	EL (%) (L=4D)
760 Min	18 Min

TYPICAL APPLICATIONS

Pumps and valves, corrosion / wear resisting parts and process equipment for use in offshore oil and gas industries, pulp, paper and textile industries, and chemical and petrochemical plant.

MATERIALS TO BE WELDED

- SAF 2507, ASTM S-32750, S-32760
- ASTM A351, A744 (cast) - CD4MCu, UNS J93370.
- ASTM A240 (wrought) - UNS S32550
- BS 3146- ANC 21, BS 3100 332C13
- DIN 1.4515, 1.4517
- Steel EN 1.4410, NF 23CND 25-06AZ, SS2328

MICROSTRUCTURE:

In the solution treated condition the micro- structure is duplex with about 30-60% ferrite dependent upon dilution.

INTERPASS TEMPERATURE: 100°C max

HEAT INPUT : 0.5 - 1.5 kJ/mm

SCALING TEMPERATURE: Approx 850°C (air)

CORROSION TEMPERATURE

Very good resistance to pitting and stress corrosion cracking in Chloride containing environments. Pitting resistance in accordance with ASTM G-48A better than 40°C.

PACKING PARAMETERS

Size (mm)	Length (mm)	Packing / Pkt (kg)	Packing / Box (kg)
1.6	1000	5	5 x 4 = 20
2	1000	5	5 x 4 = 20
2.40 / 2.50	1000	5	5 x 4 = 20
3.15 / 3.20	1000	5	5 x 4 = 20