

GFC 81K2

IDENTIFICATION

GFC 81K2, E81T1K2C

CLASSIFICATION

AWS/SFA 5.29: E81T1-K2C,
KS D7104 YFL-C506R, JIS Z3313 VFL-C506R

DESCRIPTION

GFC 81K2 is designed for welding of 590 MPa high tensile steel with slow freezing slag system. Typical applications include machineries, shipbuilding, offshore structures, bridges and general fabrications. Tubular rutile flux-cored all position wire for single or multipass welding of carbon, carbon-manganese steels and similar types of steels, including fine grain ones, with CO₂ shielding gas. The good weldability in all positions, excellent bead appearance, less spatter, a fast freezing and easy to remove slag.

WELD METAL ANALYSIS (RANGE) %

C	Mn	Si	S	Cr	P	Ni	Mo
0.15 max	1.75 max	0.39 max	0.030 max	0.15 max	0.03 max	1.0 - 2.0	0.35 max

MECHANICAL PROPERTIES (RANGE)

PWHT	UTS (MPa)	YS (MPa)	EL (%) (L=4D)	CVN Impact Value	
				Temp	Joules
As welded	600 min	530 min	19 min	-30°C	60

TYPICAL APPLICATIONS

- Ship building, railways wagons, general fabrication welding, pipe welding, bridges, automobile parts, tanks etc.
- Welding of high tensile steel offshore structure, etc.
- A537 Class 1 steel

SHIELDING GAS : CO₂

FLOW RATE : 15 - 20 l/min

PACKING PARAMETERS

Size (mm)	Amps DC (+)	Voltage	Weight / Spool (kg)
1.2	180 - 300	24 - 36	15