

# GRIBINOX 175

**IDENTIFICATION:** GRIBINOX 175

**CLASSIFICATION:** AWS/SFA 5.4 E 630-15

**CHARACTERISTICS:**

A basic coated special electrode developed for welding high strength martensitic precipitation hardening steels. The deposited weld metal is of X-ray quality.

**TYPICAL APPLICATION:**

For welding high strength martensitic stainless steels, precipitation hardened by additions of copper.

**Application include:-**

- PUMP SHAFTS
- IMPELLERS
- HYDRAULIC EQUIPMENT
- used in :-
- OIL & GAS INDUSTRIES
- PETRO-CHEMICAL PLANTS
- MARINE & NUCLEAR ENGINEERING.

**WELD METAL ANALYSIS (RANGE) %**

<b>C</b>	<b>Mn</b>	<b>Si</b>	<b>S</b>	<b>Mo</b>
0.05 max	0.35-0.70	0.7 max	0.03 max	0.3 max
<b>P</b>	<b>Cr</b>	<b>Ni</b>	<b>Cu</b>	<b>Nb</b>
0.035 max	16 16.75	4.5 5.5	3.25	0.15- 0.3

**MECHANICAL PROPERTIES (TYPICAL):**

**After PWHT, 1035±10°C for 1 hr, and then**

**Precipitate hardening at 610-630° C for 4 hrs**

**Followed by air cooling to ambient temperature**

<b>UTS MPa</b>	<b>ELN (%) (L=5D)</b>
950	12

---

**MATERIALS TO BE WELDED:**

Precipitation hardening steel such as:

- ASTM type 630
- 17-4PH(Armco Steel)
- Custom 630 (Carpenter Technology)
- ASTM A747 CB-7Cu-1, CB-7Cu-2 (cast alloys)

**MICROSTRUCTURE:**

In the PWHT condition the microstructure consists of precipitation hardened tempered martensite with some retained austenite.

**REDRYING:** 300oC /2 hrs. max 5 cycles, 10 hr. total.

**RECOMMENDED CURRENT AND PACKING DATA:**

<b>SIZE (mm)</b>	<b>LENGTH (mm)</b>	<b>AMPS DC (+)</b>	<b>PACKING/BOX (KG)</b>	<b>WEIGHT/1000 Pcs (KG)</b>
2.5	350	70-110	2X5=10	20.5
3.15	350	80-140	2X5=10	32
4	350	100-180	2X5=10	51