

# GRIDUCT T300

## IDENTIFICATION

Griduct T300, E 11018G

## CLASSIFICATION

AWS/SFA 5.5 : E 11018G IS: E76BM329Fe

DIN: 8529-81~EY 6977 Mn2NiMoBH5 BS : 2493-85 2NiMOB

## DESCRIPTION

An extruded heavy coated Hydrogen controlled Low-alloy, High Tensile Electrode. The electrode works in all position gives very little spatter with an easily removable slag leaving a bead of nice appearance. The deposition efficiency is approx. 110%.

## WELD METAL ANALYSIS (RANGE) %

C	Mn	Si	S	P	Ni	Cr	Mo	V	Cu
0.09 max	1.3 - 1.8	0.5 max	0.02 max	0.02 max	1.8 - 2.5	0.25 - 0.40	0.25 - 0.50	0.05 max	0.20 - 0.40

## MECHANICAL PROPERTIES (RANGE)

TS (N/mm <sup>2</sup> )	YS (N/mm <sup>2</sup> )	EL (%) (L=4D)	CVN Impact Value	
			Temp	Joules
760 - 840	680 - 760	20 min	27°C	157
			-51°C	34

## TYPICAL APPLICATIONS

- Penstock, earth moving equipments and heavy steel Fabrications made from high tensile steel.
- For welding USS -T1 steel, WEL -TEN 80 steels, SA 517 grade F and their equivalents. Specially recommended for welding ASTM AS17 Gr F Q&T steel.
- Excellent for welding fully killed fine grained steels and W36HI Tensile Steel.

## WELDING PROCEDURE

Use short arc length. Weaving of electrodes, if necessary should be done at slow speed and keeping a short arc. The electrodes should be used in perfectly dry condition. The electrodes should be dried at 400°C for 1 hour to obtain better result. Maintain interpass temperature below 120°C.

**DIFFUSIBLE HYDROGEN CONTENT :** 4.0 ml / 100 g. deposited metal (maximum)

## WELDING POSITION :



## PACKING PARAMETERS

# GWELD

Size (mm)	Length (mm)	Amps AC (90V) / DC (+)	Packing / Box (kg)	Packing / Box (Pcs)
2.5	350	60 - 85	5 x 4 = 20	160 x 4 = 640
3.15 / 3.20	450	90 - 130	5 x 4 = 20	110 x 4 = 440
4	450	140 - 190	5 x 4 = 20	70 x 4 = 280
5	450	190 - 250	5 x 4 = 20	45 x 4 = 180