

GRITINOX 308L

IDENTIFICATION

GRITINOX 308L E308L-17

CLASSIFICATION

AWS/SFA 5.4 E308L-17 BS 2926 E19.9.L.R,
DIN 8556 E199LR26

DESCRIPTION

A rutile flux coated electrode designed for the welding of low carbon 18% Cr / 10% Ni, type 304L, 304 austenitic stainless steel. Operability is excellent with a low spatter arc, producing a smooth weld bead surface and self-releasing slag. The deposited welds are of radiographic quality.

WELD METAL ANALYSIS (RANGE) %

C	Mn	Si	Cr	Ni	Cu	Mo	S	P
0.04 max	0.5 - 2.5	0.35 - 0.90	18 - 21	09-Nov	0.75 max	0.75 max	0.03 max	0.04 max

MECHANICAL PROPERTIES (RANGE)

UTS (MPa)	EL (%) (L=4D)	CVN Impact Value	
		Temp	Joules
525 - 630	35 - 45	0°C	60 - 100

TYPICAL APPLICATIONS

- For welding ASTM/ASME 304, 304L, 304LN, Cast CF3, CF8, food brewery and chemical process vessels, pipelines and nuclear engineering.
- Type 301, 302 and 303.
- Also suitable for welding type 321 stabilised stainless steel, petrochemical, power and pharmaceutical industries, paper processing plant.

CORROSION RESISTANCE

Good resistance to general and intergranular corrosion. Good resistance to oxidising acids. Not susceptible to intergranular corrosion.

MICROSTRUCTURE : Austenite with 3 to 9 FN (3-8% Ferrite) Typical 6FN.

ASME IX QUALIFICATION : QW-432 F-NUMBER 5, QW-442 A-NUMBER 8

REDRYING : 300°C / 2 hrs, max 5 cycles, 10 hr. total.

WELDING POSITION :



PACKING PARAMETERS

Size (mm)	Length (mm)	AMPS AC / DC (+)	Packing / Box (kg)	Packing / Box (Pcs)
-----------	-------------	------------------	--------------------	---------------------

2.5	350	50 - 75	2 x 5 = 10	94 x 5 = 470
3.15 / 3.20	350	80 - 120	2 x 5 = 10	60 x 5 = 300
4	350	100 - 140	2 x 5 = 10	38 x 5 = 190
5	350	130 - 210	2 x 5 = 10	24 x 5 = 120